



Description

Almost all Gaska Tape Inc. products are coated with "Acrylic Pressure Sensitive Adhesives". They offer performance advantages over other types of compositions. Acrylic adhesives (PSAs) exhibit good

ultraviolet and exterior durability, excellent chemical resistance and a broad range of service temperatures. These adhesives are characterized or defined by Tack, Peel, and Shear.

TACK: Is a measure of an adhesive's immediate hardness. The most common form of characterization is finger tack or "thumb appeal." More formal measurements are polyken, loop or rolling ball tack.

PEEL: Is a measure of an adhesive's ability to wet out a surface and subsequently adhere to the substrate. The most common way peels are measured is by 90 degree or 180 degree data on a particular substrate after a certain dwell time. Gaska Tape Inc. normally reports 180 degree peel data per ASTM D-1000 or PSTC-101 in pounds per linear inch.

SHEAR: Is a measure of an adhesive's vertical holding power. It is generally measured by attaching a specific surface area of adhesive to a substrate, attaching a known weight to the adhesive and carrier, then measuring the amount of time the adhesive would hold the weight. Gaska Tape Inc. generally reference PSTC-107 and report minutes or hours an adhesive would hold a 1000 gram weight to a 1 inch square of foam or film to stainless steel or glass and stainless steel.

Water Based Acrylic Emulsion Adhesive

- Emulsion acrylics consist of acrylic emulsion polymers modified with tackifiers' surfactants, wetting agents, rheology control, foam and air release and other ingredients that enhance performance and coat ability.
- Offer relative safety in handling, processing and waste disposal.
- Less costly in equipment demands and raw material requirements.
- Process relatively slower than other types like solvent based and hot melts.
- Offer some formulating latitude for performance properties, but not as much as Solvent Based Adhesives (PSAs).

Acrylic Solvent Based Adhesive

- Solvent-based acrylics are acrylic polymer solutions in organic solvent blends. These solutions contain chemical cross linkers which polymerize or crosslink the polymers as the solvent volatilizes. Other additives may include tackifiers, coating enhancements and secondary cross linkers.
- Relatively expensive in cost, processing requirements and handling. Adhesive costs are 30% to 70% more than emulsion adhesives and equipment demands for explosion-proof electrical motors, wiring, static control, exhausting and treatment of volatiles. Waste disposal is potentially prohibitive.
- Generally process faster than water-based adhesives and solvents require less dry film weight to achieve performance characteristics.
- Offer a wide range of formulating latitude to achieve performance characteristics.

Adhesive Descriptions and Performance Summary

A TYPE: Is a lower cost, general-purpose aggressive, soft high peel, low shear acrylic pressure-sensitive adhesive. This adhesive exhibits adhesion to a wide variety of surfaces. A type adheres well to stainless steel, aluminum, glass, cold rolled steel, painted metal and some plastics (e.g. acrylic, ABS, etc.). A type adhesive is approved for many automotive grade applications and general industrial uses.

B TYPE: Is a specialty, higher cost, medium peel, low shear modified acrylic pressure sensitive adhesive able to bond to some of the most difficult to adhere to rubber and rubber like products.

D TYPE: Is a low cost, medium to high peel, low shear tackified acrylic pressure sensitive adhesive designed to adhere vinyl foams to a variety of materials where no to low stress is involved.

E TYPE: Is a low cost, high peel, moderate shear tackified acrylic pressure sensitive adhesive designed to adhere to low energy foams such as polyethylene, polypropylene and polystyrene.

G TYPE: Is a specialty low cost, low to medium peel, low shear acrylic pressure sensitive adhesive. This adhesive exhibits good adhesion to oily metals (common with galvanized metals). It can be used in applications where performance at lower temperatures (to-40F) is desired.

L TYPE: Is a high cost, high peel, and moderate shear tackified acrylic pressure-sensitive adhesive modified to adhere to low surface energy surfaces like Polyethylene, Polypropylene, some ABS and other composite plastics.

M TYPE: Is a lower cost, low to medium peel, higher shear acrylic pressure sensitive adhesive. This adhesive exhibits resistance to chemical migration, has good aging properties and a higher temperature range (up to 250F). Common applications include laminations of various materials (e.g. vinyl, polyester, polypropylene, polystyrene, etc.).

S TYPE: Is a high cost, moderate peel, and high shear acrylic pressure sensitive adhesive. This adhesive exhibits resistance to chemical migration and has good aging properties on vinyl. Possible applications include window glazing, spacers for silicone sealant curtain wall construction and temperature requirements up to 250F.

Test data was derived from coating the above adhesives on a 1 mil polyester film at a target coat weight of 2.6 dry mils. Peel data was determined on stainless steel after 20 minute dwell per ASTM D1000. Shear data was determined using 1000 grams per square inch according to PSTC 107.

Adhesive Peel And Shear Strength

Adhesive	Peel Strength	Shear Strength
A Type	5.0 lbs/Linear Inch	180 Minutes
B Type	2.2 lbs/Linear Inch	60 Minutes
D Type	3.0 lbs/Linear Inch	150 Minutes
E Type	5.5 lbs/Linear Inch	1,000 Minutes
G Type	1.9 lbs/Linear Inch	30 Minutes
L Type	3.0 lbs/Linear Inch	2,500 Minutes
M Type	2.0 lbs/Linear Inch	10,000 Minutes
S Type	3.0 lbs/Linear Inch	10,000 Minutes

Warranty

Gaska Tape Inc.® warrants its product to be free from defects in material and workmanship for a period of twelve (12) months beginning on the date of invoice, provided the purchaser installs and uses the products according to any instructions provided by Gaska Tape Inc. Any product which fails during the warranty period due to a defect will be replaced.

Upon request, Gaska Tape Inc.® will be pleased to provide a copy of its written Limited Warranty with complete details of coverage, conditions and limitations.

Gaska Tape Inc.® makes no other warranty, expressed or implied, and specifically disclaims and disavows any implied warranty of merchantability and of fitness for a particular use.

International Inquiries:
Phone: 00-574-294-5431

1810 W. Lusher
P.O. Box 1968
Elkhart, IN 46515-1968

 **Gaska Tape Inc.®**
INNOVATORS IN FOAM AND TAPES
www.gaska.com

Phone: 574-294-5431
Fax: 574-293-4504
Toll free: 800-423-1571
email: sales@gaska.com