

Gaska Tape Inc. INNOVATORS IN FOAM AND TAPES

V1100 Series **Medium Density**

DESCRIPTION

Gaska Tape's V1100 Series product is a medium density closed-cell Polyvinyl Chloride foam. This tape provides an excellent combination of flexibility and conformability with strength and wear resistance. Performs in those "tough duty" applications where a tape must still flex to fit and seal.

Characteristics common to all closed cell vinyl foam products include the ability to make a long life seal against air, moisture, light and dust penetration when compressed 30% or more.

ROLL SIZES

Available Thicknesses: .063" - .500" (1.6mm - 12.7mm) V1110 .079" - .250" (2.0mm - 6.4mm) V1115 V1110BK .063" - .500" (1.6mm - 12.7mm) A1110BK .063" - .500" (1.6mm - 12.7mm) Available Widths: .250" - 57" (6.4mm - 1448mm)

Available Lengths: 15' - 302' (4.6m- 92m)

PERFORMANCE CHARACTERISTICS

- · Absorbs shocks, cushions, deadens sound and eliminates excess vibration.
- · Excellent dimensional stability and cushion against heavy loads.
- · "Swirl-Free" foam that won't move, twist, or displace when penetrated by mechanical fasteners.
- · Permits clean die cuts and ease of penetration by fasteners.
- V1100 Series is cast on a 5 mil super calendered kraft 83# clay coated paper.
- V1115 is cast on a 2 mil polyester film to provide dimensional stability, and is a self-wound product.
- A1100 / V1100BK Series is a self-extinguishing formulation and meets FMVSS 302A.
- The A1100 / V1100BK Series is specifically formulated to meet automotive specifications- see Gaska Tape Automotive Products on our website.
- V1100 Series gray color standard. The A1100/V1100BK Series black color standard, other colors available upon request.
- Sulfur-Free

Test Method-Typical Physical Properties		V1100	Additiona
ASTM D-1667	Density	11 lbs/ft ³ 176 kg/m ³	You will find the
ASTM D-2240	Hardness (shore 00)	28	our website help our products an Product De
ASTM D-1667	Compression Deflection @ 25%	5 psi	
		34 kPa	
ASTM D-1667	Compression Set @ 25%	17 %	
GTP ⁽¹⁾	Water Absorption (% by volume)	1.3 %	Die Cutting
ASTM D-412	Tensile Strength	50 psi	Standard L
		345 kPa	Standard F Manufactu
ASTM D-412	Percent Elongation	130	
ASTM C-518	Thermal Conductivity (K Factor)	0.28 btu-in./hr-ft ² .°F	
		0.040 W/mK	Vinyl Foar Market & Applic
	Recommended Service Temperature	-30 - 200 °F	
		-35 - 90 °C	
	Recommended Application Temperature	50 - 110 °F	available on ou
		10 - 45 °C	Please email us
(1) Cooke Tope Breadure			FICASE EIIIdii US

al Information:

ne following pages on elpful as you consider nd configurations.

> escription g Descriptions Lead Times Product List uring Tolerances m Typical Properties

ication info. is also ur Website.

us for more information: salesorders@gaska.com

(1) Gaska Tape Procedure

Data is intended as a guide only and is presented without guarantees and without assumption of liabilities resultant from the use of information provided. This data is not to be used for specification purposes.

WARRANTY

Gaska Tape Inc.® warrants its product to be free from defects in material and workmanship for a period of twelve (12) months beginning on the date of invoice, provided the purchaser installs and uses the products according to any instructions provided by Gaska Tape Inc. Any product which fails during the warranty period due to a defect will be replaced.

Upon request, Gaska Tape Inc.® will provide a copy of its written Limited Warranty with complete details of coverage, conditions and limitations.

Gaska Tape Inc.® makes no other warranty, expressed or implied, and specifically disclaims and disavows any implied warranty of merchantability and of fitness for a particular use.

Manufactured in the USA Phone: 574-294-5431 International Inquiries: Toll Free: 800-423-1571 1810 W. Lusher Ave. Phone: 00-574-294-5431 www.gaska.com 574-389-9701 P.O. Box 1968 Fax: 574-293-4504 Elkhart, IN 46515-1968 Email: salesorders@gaska.com