

# LC700 Series

## **Low Compression**



### DESCRIPTION

Gaska Tape's LC700 Series products are excellent alternatives to low permeability urethane where long product life is critical. This foam is excellent for use in applications requiring a low force to compress.

This low compression series is specially formulated, soft, closed-cell Polyvinyl Chloride foam that can be produced with or without adhesive on one side. It can also be cast on a permanent polyester film to the opposite side.

## **ROLL SIZES**

Available Thicknesses:

**LC710** .079" - .787" (2.0mm - 20mm) **LC715** .125" - .500" (3.2mm - 12.7mm)

Available Widths:

.250" - 57" (6.4mm - 1448mm)

Available Lengths: 25' - 30' (7.6m - 9.1m)

## PERFORMANCE CHARACTERISTICS

- Conforms to irregular surfaces and curves.
- Alternative to low perm urethane where longer product life is necessary.
- Used in conjunction with thin gauge plastics and sheet metal to prevent over-bowing or over-flexing.
- High-tack (A3) adhesive has a wide service temperature range.
- Also available with G3 adhesive, specifically designed to adhere to galvanized metals.
- LC700 Series is a self-extinguishing formulation and meets FMVSS 302A.
- LC710 is cast on a 7 mil clay coated paper.
- Specifically formulated to meet automotive specifications- see Gaska Tape Automotive Products on our website.
- LC715 is cast on a 2 mil polyester film to provide dimensional stability, and is a self-wound product.
- Black color standard, other colors available upon request.
- Sulfur-Free

Test Method-Typical Physical Properties		LC700
ASTM D-1667	Density	7 lbs/ft <sup>3</sup>
		112 kg/m <sup>3</sup>
ASTM D-2240	Hardness (shore 00)	10
ASTM D-1667	Compression Deflection @ 25%	0.5 psi
		3.5 kPa
ASTM D-1667	Compression Set @ 25%	4 %
GTP <sup>(1)</sup>	Water Absorption (% by volume)	3.2 %
ASTM D-412	Tensile Strength	20 psi
		138 kPa
ASTM D-412	Percent Elongation	150
ASTM C-518	Thermal Conductivity (K Factor)	0.27 btu-in./hr-ft <sup>2</sup> -°F
		0.039 W/mK
	Recommended Service Temperature	-40 - 180 °F
		-40 - 82 °C
	Recommended Application Temperature	50 - 110 °F
		10 - 45 °C

## (1) Gaska Tape Procedure

Data is intended as a guide only and is presented without guarantees and without assumption of liabilities resultant from the use of information provided. This data is not to be used for specification purposes.

#### Additional Information:

You will find the following pages on our website helpful as you consider our products and configurations.

Product Description
Die Cutting Descriptions
Standard Lead Times
Standard Product List
Manufacturing Tolerances
Vinyl Foam Typical Properties

Market & Application info. is also available on our Website.

Please email us for more information: salesorders@gaska.com

### WARRANTY

Gaska Tape Inc.® warrants its product to be free from defects in material and workmanship for a period of twelve (12) months beginning on the date of invoice, provided the purchaser installs and uses the products according to any instructions provided by Gaska Tape Inc. Any product which fails during the warranty period due to a defect will be replaced.

Upon request, Gaska Tape Inc.® will provide a copy of its written Limited Warranty with complete details of coverage, conditions and limitations.

Gaska Tape Inc.® makes no other warranty, expressed or implied, and specifically disclaims and disavows any implied warranty of merchantability and of fitness for a particular use.

1810 W. Lusher Ave. P.O. Box 1968 Elkhart, IN 46515-1968 Manufactured in the USA

www.gaska.com Email: salesorders@gaska.com Phone: 574-294-5431 Toll Free: 800-423-1571 Fax: 574-389-9701

574-293-4504

International Inquiries: Phone: 00-574-294-5431

Rev 03/2023