

# V2500 Series

## **Heavy Density**



### DESCRIPTION

Gaska Tape's V2500 Series product is a heavy density closed-cell Polyvinyl Chloride foam. Designed for use in the most demanding foam sealing or cushioning applications. High internal strength resists pressure from outside forces and high hardness resists deterioration.

Characteristics common to all closed cell vinyl foam products include the ability to make a long life seal against air, moisture, light and dust penetration when compressed 30% or more.

## **ROLL SIZES**

Available Thicknesses:

**V2510** .031" - .250" (0.8mm- 6.4mm) **V2515** .039" - .188" (1mm – 4.8mm) **V2520** .031" - .250" (0.8mm – 6.4mm)

Available Widths:

.250" - 57" (6.4mm - 1448mm)

Available Lengths: 25' - 302' (7.6m- 92m)

## PERFORMANCE CHARACTERISTICS

- Our strongest standard V Series foam cushions, absorbs shock, and resists wear and abrasion in the most demanding applications.
- Swirl free for smooth fastener penetration.
- · Insulates against temperature.
- V2500 Series is a self-extinguishing formulation and meets FMVSS 302A.
- V2510 is cast on a 5 mil 83# super calendered kraft paper.
- V2520 is cast on a 5 mil 84# polycoated 2 sided brown kraft paper.
- Die or kiss cutting material is available on 84# polycoated release paper or 12pt release board.
- Specifically formulated to meet automotive specifications- see Gaska Tape Automotive Products on our website.
- V2515 is cast on a 2 mil polyester film to provide dimensional stability, and is a self-wound product.
- Black color standard, other colors available upon request.
- Sulfur-Free

Test Met	hod- Typical Physical Properties	V2500
ASTM D-1667	Density	25 lbs/ft <sup>3</sup> 400 kg/m <sup>3</sup>
ASTM D-2240	Hardness (shore 00)	58
ASTM D-1667	Compression Deflection @ 25%	14 psi 96 kPa
ASTM D-1667	Compression Set @ 25%	6 %
GTP <sup>(1)</sup>	Water Absorption (% by volume)	1.2 %
ASTM D-412	Tensile Strength	130 psi 900 kPa
ASTM D-412	Percent Elongation	110
ASTM C-518	Thermal Conductivity (K Factor)	0.33 btu-in./hr-ft²-°F 0.048 W/mK
	Recommended Service Temperature	-40 - 180 °F -40 - 82 °C
	Recommended Application Temperature	50 - 110 °F 10 - 45 °C

#### (1) Gaska Tape Procedure

Data is intended as a guide only and is presented without guarantees and without assumption of liabilities resultant from the use of information provided. This data is not to be used for specification purposes.

#### Additional Information:

You will find the following pages on our website helpful as you consider our products and configurations.

Product Description
Die Cutting Descriptions
Standard Lead Times
Standard Product List
Manufacturing Tolerances
Vinyl Foam Typical Properties

Market & Application info. is also available on our Website.

Please email us for more information: salesorders@gaska.com

## WARRANTY

Gaska Tape Inc.® warrants its product to be free from defects in material and workmanship for a period of twelve (12) months beginning on the date of invoice, provided the purchaser installs and uses the products according to any instructions provided by Gaska Tape Inc. Any product which fails during the warranty period due to a defect will be replaced.

Upon request, Gaska Tape Inc.® will provide a copy of its written Limited Warranty with complete details of coverage, conditions and limitations.

Gaska Tape Inc.® makes no other warranty, expressed or implied, and specifically disclaims and disavows any implied warranty of merchantability and of fitness for a particular use.

1810 W. Lusher Ave. P.O. Box 1968 Elkhart, IN 46515-1968 Manufactured in the USA

www.gaska.com Email: salesorders@gaska.com Phone: 574-294-5431
Toll Free: 800-423-1571
Fax: 574-389-9701
574-293-4504

International Inquiries: Phone: 00-574-294-5431

Rev 03/2023